Lark Engineering Company (India) Pvt. Ltd.

I.T.I. Sasouli Road, Yamuna Nagar - 135 001 (Haryana)

Form No.	CNC/QA/FM/03
Rev. No.	01
Rev. Date	31-07-2013

Final Inspection (Pellet Dies) after Hardening & Finishing

S.No.	Check Parameter	Specification / Observations	Remarks
1.	Work rder No.	13123	36145
2.	Visual Inspection	ok - 6.0 mm (Sew)	302 Rev Bright
3.	Pellet Die No.	13283	07- ok
4	Hardened by	Lark firm	Relief - ok
5	Received by after hardening (Name)	Jaspal	(2.2) 15 mm
6	Hardness achieved on 1st side	50.1 - 50.2 HRC	Relief 8.5, 9 mm
7	Hardness achieved on 2nd side	50.1 - 50.2 HRC	Counter ok
8	Ovalty aftery hardening 1st side	(0.1) mm	PCD - 454 mm
9	Ovalty aftery hardening 2nd side	(0.2) mm	Tapping Φ 3/4"
10	Outside Diameter	570 mm	Deep - 18.6 mm
11	Inside Diameter	420 mm	Tapping No of
12	Width of die	~~182 mm~~ 173 mm	Holes - 8
	Inspected By (Sign) & Date	Jaspal 30/10/24	
1.	Finish Fitting size 1st side	488.7 +.12 +.12 mm	
2.	Finish Fitting size 2nd side	488.7 +.10 +.11 mm	
3.	Finish size made by		
	Inspected By (Sign) & Date	Jaspal 30/10/24	
1.	Supplied to (Customer Name)	Annual feeds Bihar	
2.	Dispatch Date		
	Reported By (Sign) & Date	Jaspal 30/10/24	

Satish 30/10/24,

Reviewed by (Engineer-CNC)

Manager-CNC

100x2 - CW:PIIK

Scanned with CamScanner